



Europäisches Patentamt
European Patent Office
Office européen des brevets

Publication number:

**0 177 791
A2**

EUROPEAN PATENT APPLICATION

Application number: 85111514.7

Int. Cl.: **C 09 D 3/80, C 08 F 220/00,
C 08 F 299/02**

Date of filing: 12.09.85

Priority: 13.09.84 JP 191936/84

Applicant: **SUMITOMO METAL INDUSTRIES, LTD., 15, Kitahama 5-chome Higashi-ku, Osaka-shi, Osaka, 541 (JP)**
Applicant: **Nippon Paint Company, Ltd, 2-1-2, Oyodokita Oyodo-ku, Osaka-shi Osaka-fu (JP)**

Inventor: **Yamada, Koichi, 13 Yawata Baba, Yawata-shi Kyoto-fu (JP)**

Inventor: **Sumiyoshi, Iwao, 2-6-16, Aikawa Higashiyodogawa-ku, Osaka (JP)**

Inventor: **Ishihara, Ryoji, 2-15-505, Nakamiyakitamachi, Hirakata-shi Osaka-fu (JP)**

Inventor: **Ohkita, Masakazu, No. 502, 1-8-31 Minamitanabe, Higashisumiyoshi-ku Osaka (JP)**

Inventor: **Arai, Tetsuzo, 16-11 Sakasedai 4-chome, Takarazuka-shi Hyogo-ken (JP)**

Inventor: **Yoshiiwa, Masanori, 256-16 Nishinosho, Wakayama-shi Wakayama-ken (JP)**



Date of publication of application: 16.04.86
Bulletin 86/16

Representative: **Kinzebach, Werner, Dr., Patentanwälte Reitzstötter, Kinzebach und Partner Bauerstrasse 22, D-8000 München 40 (DE)**

Designated Contracting States: **DE FR GB IT**

Radiation curable primer coating compositions.

A radiation curable primer coating composition is provided comprising (a) a reaction product of an epoxide compound and an ethylenically unsaturated monocarboxylic acid, (b) a compound of the formula:



wherein R is hydrogen atom or methyl, A is a C₂-C₄ alkylene group, and n is 0, 1 or 2; and (c) a compound having at least one epoxy group per molecule.

The composition may be applied onto a steel substrate and cured by the irradiation of an actinic radiation for improving properties of subsequently applied polyolefin coatings thereon.

EP 0 177 791 A2

0177791

BACKGROUND OF THE INVENTION

5 This invention relates to a radiation curable primer coating composition suitable for use in forming a polyolefin coating on a steel substrate.

 Polyolefin coated steel pipes have been widely used as pipelines for conveying petroleum or natural gas.

10 Since most of these pipelines are subjected to severe environmental conditions, high levels of adhesive and anticorrosive characteristics are required for the polyolefin coating layer.

 Polyolefin resins are nonpolar and have crystalline
15 nature and thus exhibit excellent chemical stability and excellent mechanical properties. However, their adhesion strength to a steel substrate are generally poor when polyolefin coatings are applied directly. It is for this reason that an adhesive layer consisting of a modified polyolefin
20 such as ethylene-acrylic acid copolymers or ethylene-maleic anhydride copolymers is interposed between the polyolefin protective layer and the steel substrate. This modified polyolefin layer exhibits an excellent adhesion strength to the substrate but this adhesion strength tends to decrease
25 as the coated products are exposed to severe corrosive environment. In order to avoid this usually epoxy based

0177791

primers are applied on the substrate surface. Thus the entire operation for producing polyolefin coated steel pipes include the steps of polishing the substrate surface to remove oxide films using such techniques as sand blasting or
5 shot blasting, subjecting to a surface treatment such as chromate treatment if necessary, applying the epoxy primer, and curing the primer by heating to a temperature from 130°C to 200°C using an induction heater or hot air oven.

After the applied primer coating has been fully cured so
10 that the coating film is not easily scratched or peeled off when contacted by conveying rolls, the pipes are passed to next conveying rolls for extrusion coating the interposing adhesive layer and the polyolefin outer layer successively.

Epoxy primer compositions currently used for this
15 purpose require heating to a temperature above 130°C for about 3 to 4 minutes. This limits the productivity of polyolefin coated steel pipes when the coating is carried out while continuously conveying pipes axially. In order to convey substrate pipes smoothly, the distance between adja-
20 cent conveying rolls should be less than one half of the pipe length. Assuming that the distance between adjacent conveying rolls is 3 m and a curing time of 3 minutes is required for curing the epoxy primer coating, the conveying speed is limited to less than 1 m/minute.

25 In addition to low productivity, a substantial amount of heat energy is required for heating steel pipes.

It is therefore a principal object of the present invention to provide a primer coating composition free from these disadvantages for use in improving the adhesion strength of polyolefin layers to a steel substrate.

5 It is another object of the present invention to provide a primer coating composition of the above-mentioned type which cures within a very short length of time by irradiating an actinic radiation.

Other objects and advantages of the present invention will become apparent as the description proceeds.


SUMMARY OF THE INVENTION

According to the present invention, there is provided a primer coating composition which cures upon irradiation of an actinic radiation for improving the adhesion strength of polyolefin-based coating layer to a steel substrate.

The composition comprises:


(a) a reaction product of an epoxide compound and an ethylenically unsaturated monocarboxylic acid (hereinafter referred to as "unsaturated epoxy ester");

(b) a compound of the formula:



25 or

0177791



wherein R is hydrogen atom or methyl, A is a C₂-C₄ alkylene group, and n is 0, 1 or 2; and

(c) a compound having at least one epoxy group per molecule. The proportions of said components (a), (b) and (c) are preselected to give a cured coating film having a glass transition temperature higher than 45°C.

The composition may additionally contain a liquid monomer and/or oligomer capable of polymerizing upon irradiation of an actinic radiation.

The use of the primer coating composition of the present invention enables to significantly decrease the length of time required for curing the primer coating by the irradiation of an actinic radiation. Thus, the productivity of polyolefin coated steel pipes, for example, may be greatly increased and a large amount of heat energy required for preheating substrate pipes and/or thermally curing the primer coating may be saved.

DETAILED DESCRIPTION OF THE INVENTION

(a) Unsaturated epoxy esters:

Unsaturated epoxy esters constituting component (a) may be produced by reacting an epoxide compound with an ethylenically unsaturated monocarboxylic acid.

0177791

Examples of epoxide compounds include a reaction product of bisphenol A and epichlorohydrine or methyl-epichlorohydrine (hereinafter collectively referred to as "(methyl)epichlorohydrine"); a reaction product of bisphenol
5 A and/or bisphenol F, resorcinol and (methyl)epichlorohydrine; a reaction product of novolak or resol typed phenol-formaldehyde condensate and (methyl)epichlorohydrine; a reaction product of a polyol and (methyl)epichlorohydrine; a reaction product of a polybasic acid and (methyl)epichlorohydrine;
10 a reaction product of a polyalkylene glycol and (methyl)-epichlorohydrine and the like.


These epoxide compounds may be reacted with a monobasic and/or dibasic carboxylic acid free of ethylenic unsaturation such as acetic acid, propionic acid, benzoic
15 acid, succinic acid, adipic acid, dimer acid or phthalic acid using the epoxide compound in large excess so that the reaction product has at least one remaining epoxy group per molecule. The term "epoxide compound" as used herein include such reaction products as well.

20 Examples of ethylenically unsaturated monocarboxylic acid include acrylic acid, methacrylic acid, crotonic acid, cinnamic acid, itaconic acid monoalkyl esters such as methyl or ethyl ester and mixtures of these acids.

The unsaturated epoxy ester of component (a) may be
25 prepared by reacting the epoxide compound and the ethylenically unsaturated monocarboxylic acid in about stoichiometric

amounts. The reaction may be carried out by heating reactants at a temperature from 100°C to 130°C preferably in the presence of a catalytic amount of a tertiary amine such as N,N-dimethylaniline, pyridine, triethylamine, hexamethylenediamine or N,N-dimethylaminoethyl methacrylate. The reaction may be continued for 5 to 10 hours to give the desired unsaturated epoxy ester (a).

(b) Compounds of the formula



15 Examples of compounds of the above formula include dicyclopentenyl acrylate or methacrylate (hereinafter collectively referred to as "(meth)acrylate"), dicyclopentyl (meth)acrylate, dicyclopentenyl oxyethyl (meth)acrylate, dicyclopentyl oxyethyl (meth)acrylate, dicyclopentenyl oxypropyl (meth)acrylate, dicyclopentyl oxypropyl (meth)acrylate, dicyclopentenyl ethoxyethyl (meth)acrylate, dicyclopentyl ethoxyethyl (meth)acrylate and the like.

20

These compounds have a bulky structure and are useful to impart a relatively high glass transition temperature (T_g) to the fully cured coating film resulting from the primer composition of the present invention.

25

(c) Compounds having at least one epoxy group in the molecule:

The same epoxide compounds as used for synthesizing unsaturated epoxy esters (a) may be employed as component (c).
5 Component (c) is used in an amount at least equal to a stoichiometric amount relative to the acid number of component (a) corresponding to the residual free carboxylic groups. By adding this component, the anti-alkali property of the resulting coating film may be enhanced.

10 The proportions of components (a), (b) and (c) are preferably 40-80 parts/20-60 parts/1-15 parts on weight basis.

The primer coating composition of the present invention may additionally contain a liquid monomer and/or oligomer capable of curing upon the irradiation of an actinic
15 radiation.

Examples of monomers include methyl (meth)acrylate, ethyl (meth)acrylate, n-butyl (meth)acrylate, isobutyl (meth)acrylate, n-hexyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, cyclohexyl (meth)acrylate, benzyl (meth)acrylate, 2-hydroxyethyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate,
20 2-methoxyethyl (meth)acrylate, 2-ethoxyethyl (meth)acrylate, carbitol (meth)acrylate, dipropylene glycol monomethyl ether mono(meth)acrylate, triethylene glycol monomethyl ether mono(meth)acrylate, tetrahydrofuryl (meth)acrylate, styrene, α -
25 methylstyrene, vinyltoluene, ethylene glycol di(meth)acrylate, diethylene glycol di(meth)acrylate, propylene glycol di(meth)

0177791

acrylate, 1,6-hexanediol di(meth)acrylate, neopentyl glycol di(meth)acrylate, trimethylpropane tri(meth)acrylate and the like.

5 Examples of oligomers include unsaturated polyesters such as a condensate of phthalic acid, diethylene glycol and acrylic acid, and unsaturated polyurethanes such as produced by reacting one mole of trimethylolpropane, 3 moles of tolylenediisocyanate and 3 moles of 2-hydroxyethyl (meth) acrylate.

10 These monomers and oligomers are used for adjusting the viscosity of the primer composition and for adjusting Tg of the resulting film. However, excessive use of these monomers and/or oligomers tends to decrease the adhesion strength to the steel substrate. Accordingly, the combined
15 amount of these monomers and/or oligomers plus component (b) should not exceed 60 parts by weight per 100 parts by weight of the entire composition.

The proportions of above-mentioned essential and optional components are preselected so that the composition
20 gives a cured film having a Tg above 45°C. This is because polyolefin coatings applied on steel pipes, for example, require a high adhesion strength at elevated temperatures.

When the primer coating composition is cured by the irradiation of ultraviolet light, it is necessary for the
25 composition to contain a photosensitizer. Any known photosensitizer may be used including benzoin, benzoin methyl

ether, benzoin isopropyl ether, anthraquinone, 2-ethylanthraquinone, benzophenone, acetophenone, 2,2-diethoxy-2-phenylacetophenone, 2-chlorothioxanthone, 2-methylthioxanthone, benzyldimethylketal, 2-hydroxy-2-methyl-1-phenylpropan-1-one
5 and mixtures of these photosensitizers. These photosensitizers may be added in an amount from 0.1 to 2.0% by weight of the entire composition to accelerate the photochemical reaction involved.

The primer coating composition may contain, of course,
10 other conventional additives such as antifoaming agents, anti-running agents, surface conditioning agents, anticorrosive agents, fillers, colorants, solvents and the like to such a extent that these additives do not adversely affect the properties of the primer coating.

15 Any known technique may be employed for applying the primer coating composition of the present invention onto substrates such as steel pipes. These include airless spraying, roller coating, brushing, drawing and the like.

The primer coatings applied on a substrate may be
20 cured by exposing to an actinic radiation. Ultraviolet light, electron radiation, X-rays or gamma rays may be employed. Electron accelerators, Co⁶⁰, X-ray generators and UV lamps may be used as radiation sources. As a UV source, high pressure mercury lamps, low pressure mercury lamps,
25 ultra-high pressure mercury lamps, metal halide lamps or xenone lamps may be used. UV light or electron radiation is

preferable when rapid curing time is required. The curing may be carried out in the atmosphere since the inhibitory effect of air on the polymerization reaction is not substantial. However, the use of inert gas atmosphere such as nitrogen gas atmosphere is more preferable for enhancing the curability of the primer coating. The length of curing time varies depending upon the nature and intensity of radiation used. For example, by the use of a plurality of 6 kW high pressure mercury lamps placed to achieve uniform irradiation onto the coated surface, it is possible to finish the curing within 1-10 seconds.

Polyolefin coated steel pipes may be produced by the conventional method by extrusion coating the substrate first with modified polyolefin adhesive layer and then with polyolefin protective layer. Prior to applying the primer coating, the substrate surface may be provided with conventional conversion coatings such as phosphate or chromate conversion coatings by dipping the substrate in a treating bath or applying a treating liquid containing silica sol. This treatment may further improve the adhesion strength and cathodic desbonding resistance of the resulting polyolefin coated steel pipes when combined with the application of the primer coating of this invention.

The following examples are intended to illustrate the present invention in further detail. In these examples, all parts and percents are by weight.

0177791

EXAMPLE 1

A flask having a stirrer, a reflux condenser, a thermometer and a drip funnel was charged with 950 g of epichlorohydrine-bisphenol A epoxy resin (about 2 epoxy
5 equivalents), 729 g of dicyclopentenyl acrylate, 1.8 g of hydroquinone and 9.1 g of N,N-dimethylaminoethyl acrylate. The mixture was heated to 100°C. Then 144 g (2 moles) of acrylic acid was added with stirring over 1 hour and reacted for additional 5 hours at the same temperature. The acid
10 number of the resulting resin composition was 3.

EXAMPLE 2

The same flask as used in Example 1 was charged with 1900 g of epichlorohydrine-bisphenol A epoxy resin (about 2 epoxy equivalents), 1363 g of dicyclopentyl acrylate, 3.4 g
15 of hydroquinone, and 17.0 g of N,N-dimethylaminoethyl acrylate. The mixture was heated to 100°C. Then 144 g (2 moles) of acrylic acid was added with stirring over 1 hour and reacted for additional 5 hours at the same temperature. The acid number of the resulting resin composition was 3.5.

20 EXAMPLE 3

The same flask as used in Example 1 was charged with 1884 g of epichlorohydrine-bisphenol A-resorcinol epoxy resin (about 2 epoxy equivalents), 1352 g of dicyclopentenyl
25 acrylate, 3.4 g of hydroquinone and 16.9 g of N,N-dimethylaminoethyl acrylate. The mixture was heated to 100°C. Then 144 g (2 moles) of acrylic acid was added with stirring

0177791

over 1 hour and reacted for additional 5 hours at the same temperature. The acid number of the resulting resin composition was 2.8.

EXAMPLE 4

5 The flask as used in Example 1 was charged with 1884 g (about 2 epoxy equivalents) of epichlorohydrin-bisphenol A-resorcinol epoxy resin, 1352 g of dicyclopentenyl oxyethyl acrylate, 3.4 g of hydroquinone and 16.9 g of N,N-dimethyl-aminoethyl acrylate. The mixture was heated to 100°C. Then
10 144 g (2 moles) of acrylic acid was added with stirring over 1 hour and reacted at the same temperature for additional 5 hours. The acid number of the resulting resin composition was 3.1.

EXAMPLE 5

15 The procedure of Example 4 was repeated except that an equivalent amount of dicyclopentenyl oxyethoxyethyl acrylate was used as Component (b). An acid number of 3.4 was obtained.

EXAMPLE 6 (CONTROL)

20 The procedure of Example 3 was repeated except that 1352 g of carbitol acrylate was used instead of dicyclopentenyl acrylate. The acid number of the product was 2.8.

EXAMPLES 7-13 AND COMPARATIVE EXAMPLES 1-2

25 A primer coating composition shown in Table I was applied on a steel plate of 3.2X70X150 mm size having a polished surface by sand blasting. The coating film was cured by irradiating UV light. A 2 kW high pressure mercury

0177791

lamp (Japan Storage Battery Co., Ltd., Model HI-20N, light emission length 25 cm, equipped with a beam collector) was placed over a conveyer at a height of 8 cm. The coated plate was conveyed under the lamp in a direction transverse to the longitudinal axis of the lamp at a speed of 3 m/minutes.

Then a sheet of modified polyethylene (ADMER NE 050, Mitsui Petrochemical Industries, Ltd.) was heat bonded over the primer coating at 170°C to form a layer having a thickness of 300-400 microns. Finally a preheated polyethylene film (low density polyethylene film having a melt index of 1.5, a density of 0.925 and a film thickness 3-4 mm) was lined by pressing the film against the steel plate at a pressure of 0.1 kg/cm² at a temperature of 170°C for 2 minutes.

In Comparative Example 2, modified polyethylene coating was directly applied onto the sand blasted steel plate without applying any primer coating composition.

In Example 13, prior to applying the primer coating, the steel plate was preheated to a temperature of 50-60°C, coated with a chromate based conversion coating liquid (prepared by mixing an aqueous solution of CrO₃ with ethylene glycol sufficient to reduce 40% of CrO₃ and further adding thereto colloidal silica having a particle size of 14 mμ) and allowed to stand until the applied coating was dried by the latent heat of the plate. The amount of coating was 1000-1200 mg/m² after drying.

0177791

The resulting polyolefin coated plates were tested on adhesion strength and cathodic desbonding resistance according to the following methods. The results obtained are shown in Table II.

5 Test Method:

1. Primary adhesion strength

The coating was scratched to form a plurality of parallel cut lines at a distance between lines of 10 mm to the full depth of the coating. A section of cut polyethylene
10 film was peeled from the steel plate and its peel strength (adhesion strength) at 180° angle was measured at 20°C and 60°C respectively at a pulling speed of 10 mm/minutes using TENSILON tester.

2. Secondary adhesion strength

15 The same test as above was repeated except that the scratched sample was soaked in 3% saline for 1,000 hours at 60°C, taken out and tested on the peel strength at 20°C.

3. Cathodic desbonding resistance

The coated plate was provided with a plurality of
20 holes having a diameter of 5 mm through the coating layer to expose the substrate surface in these areas. Then the sample plate was placed in 3% saline at for 30 days at 20°C and a voltage was applied to the sample plate so that a potential of -1.5 volt was established relative to a standard Cu/CuSO_4
25 electrode. The degree of desbonding was judged by a distance through which a knife edge was penetrated.

0177791

Table I

Components (parts)	Primer Formulations							Comparative Ex. 1
	Ex. 7	Ex. 8	Ex. 9	Ex. 10	Ex. 11	Ex. 12	Ex. 13	
Resin Ex. 1	100							
" Ex. 2		100						
" Ex. 3			80					
" Ex. 4				100		100	100	
" Ex. 5					100			100
" Ex. 6								
NK ester ABPE-4 ¹⁾			20					
EPIKOTE 828 2)	1	1	1	1	1	3	3	1
<u>Contents (parts)</u>								
(a) Unsaturated epoxy ester	60	60	48	60	60	60	60	60
(b) DCPD ester + Monomer	40	40	32	40	40	40	40	40
(c) Epoxide	1	1	1	1	1	3	3	1
Photosensitizer ³⁾ (parts)	5	5	5	5	5	5	5	5
Tg, °C ⁴⁾	68	63	68	57	50	55	55	43

0177791

Remarks:

- 1) 2,2-bis 4-acryloyloxy-poly(ethyleneoxy)-phenyl propane,
Shin Nakamura Kagaku Kubushiki Kaisha.
- 2) Epichlorohydrine-bisphenol A epoxy resin,
Shell Chemical.
- 3) Benzoin isobutyl ether.
- 4) Measured according to TMA penetration method using
Shimadzu thermal analyzer Model DT-30.

10

15

20

25

0177791

Table II

	<u>Test Results</u>							<u>Comparative</u>	
	<u>Ex. 7</u>	<u>Ex. 8</u>	<u>Ex. 9</u>	<u>Ex. 10</u>	<u>Ex. 11</u>	<u>Ex. 12</u>	<u>Ex. 13</u>	<u>Ex. 1</u>	<u>Ex. 2</u>
<u>Primary Adhesion</u> <u>Strength (kg/cm)</u>									
at 20°C	25	27	21	24	18	20	>30	15	peeled off
at 60°C	15	18	12	16	10	12	19	peeled off	peeled off
<u>Secondary Adhesion</u> <u>Strength (kg/cm, 20°C)</u>	10	11	13	13	9	9	17	peeled off	peeled off
<u>Cathodic desbonding</u> <u>resistance (mm)</u>	8	6	10	5	5	3	1.5	9	25

0177791


As shown in Table II, polyolefin coated steel substrates having a primer coating of the present invention (Examples 7 through 13) are superior to a corresponding polyolefin coated substrate having no primer coating (Comparative Example 2) in terms of the adhesion strength and cathodic desbonding resistance. When the primer coating has a Tg less than 45°C (Comparative Example 1), the secondary adhesion strength is not satisfactory. The conversion coating of the substrate prior to the application of primer coating (Example 13) further improves the cathodic desbonding resistance.

0177791


WHAT IS CLAIMED IS:

1. A radiation curable primer coating composition for use in forming polyolefin coating on a steel substrate comprising:

- (a) a reaction product of an epoxide compound and an ethylenically unsaturated monocarboxylic acid;
- (b) a compound of the formula:



or



wherein R is hydrogen atom or methyl, A is a C₂-C₄ alkylene group, and n is 0, 1 or 2; and

- (c) a compound having at least one epoxy group per molecule; the composition containing said components (a), (b) and (c) in a preselected proportion to give a cured coating film having a glass transition temperature higher than 45°C.

2. The radiation curable primer coating composition according to Claim 1 further comprising a radiation polymerizable liquid monomer and/or oligomer.

0177791

3. The radiation curable primer coating composition according to Claim 1, wherein the ratio of said component (a):component (b):component (c) is 40-80:20-60:1-15 on weight basis.

5 4. The radiation curable primer coating composition according to Claim 2, wherein the combined amount of said component (b) and said monomer and/or oligomer is less than 60 parts per 100 parts by weight of the entire composition.

10 5. The radiation curable primer coating composition according to Claim 1, wherein said component (a) is a reaction product of an epoxy resin and acrylic acid or methacrylic acid.

15 6. The radiation curable primer coating composition according to Claim 5, wherein said component (b) is dicyclopentenyl acrylate, dicyclopentyl acrylate, dicyclopentyloxyethyl acrylate, dicyclopentyloxyethyl acrylate, dicyclopentyloxyethoxyethyl acrylate, dicyclopentyloxyethoxyethyl acrylate or corresponding esters of methacrylic acid.

20 7. The radiation curable primer coating composition according to Claim 6, wherein said component (c) is an epoxy resin.

8. The radiation curable primer coating composition according to Claim 1 further comprising a photosensitizer.

25

9. A method of forming a polyolefin protective coating on a steel substrate comprising the steps of extrusion coating the substrate with a modified polyolefin layer and then with a polyolefin protective layer successively, the improvement wherein said substrate is given a primer coating by applying the radiation curable composition of claims 1 - 8 and then irradiating an actinic radiation.

10. The method according to Claim 9, wherein said actinic radiation is ultraviolet light, and wherein the radiation curable composition of Claim 8 is employed.

11. The method according to Claim 9 further comprising the step of applying a conversion coating onto the substrate prior to the application of said primer coating.

12. The method according to Claim 9, wherein said substrate is a steel pipe or a steel sheet.



Europäisches Patentamt

European Patent Office

Office européen des brevets

(11) Publication number:

**0 177 791
A3**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 85111514.7

(51) Int. Cl.³: C 09 D 3/80

C 08 F 220/00, C 08 F 299/02

(22) Date of filing: 12.09.85

(30) Priority: 13.09.84 JP 191936/84

(72) Inventor: Sumiyoshi, Iwao
2-6-16, Aikawa Higashiyodogawa-ku
Osaka(JP)

(43) Date of publication of application:
16.04.86 Bulletin 86/16

(72) Inventor: Ishihara, Ryoji
2-15-505, Nakamiyakitamachi
Hirakata-shi Osaka-fu(JP)

(88) Date of deferred publication of search report: 28.10.87

(84) Designated Contracting States:
DE FR GB IT

(72) Inventor: Ohkita, Masakazu
No. 502, 1-8-31 Minamitanabe
Higashisumiyoshi-ku Osaka(JP)

(71) Applicant: SUMITOMO METAL INDUSTRIES, LTD.
15, Kitahama 5-chome Higashi-ku
Osaka-shi, Osaka, 541(JP)

(72) Inventor: Arai, Tetsuzo
16-11 Sakasada 4-chome
Takarazuka-shi Hyogo-ken(JP)

(71) Applicant: Nippon Paint Co., Ltd.
2-1-2, Oyodokita Oyodo-ku
Osaka-shi Osaka-fu(JP)


(72) Inventor: Yoshiwa, Masanori
256-16 Nishinosho
Wakayama-shi Wakayama-ken(JP)

(72) Inventor: Yamada, Koichi
13 Yawata Baba
Yawata-shi Kyoto-fu(JP)


(74) Representative: Kinzebach, Werner, Dr.
Patentanwälte Reitstötter, Kinzebach und Partner
Sternwartstrasse 4 Postfach 86 06 49
D-8000 München 86(DE)

(54) Radiation curable primer coating compositions.

(57) A radiation curable coating composition is provided comprising (a) a reaction product of an epoxide compound and an ethylenically unsaturated monocarboxylic acid, (b) a compound of the formula:



or



wherein R is hydrogen atom or methyl, A is a C₂-C₄ alkylene group, and n is 0, 1 or 2; and (c) a compound having at least one epoxy group per molecule.

The composition may be applied onto a steel substrate and cured by the irradiation of an actinic radiation for improving properties of subsequently applied polyolefin coatings thereon.

EP 0 177 791 A3



European Patent
Office

EUROPEAN SEARCH REPORT

0177791

Application number

EP 85 11 1514

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
A	US-A-4 178 425 (W.D. EMMONS et al.) * Claims * -----	1	C 09 D 3/80 C 08 F 220/00 C 08 F 299/02
			TECHNICAL FIELDS SEARCHED (Int. Cl.4)
			C 09 D C 08 F
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 19-08-1987	Examiner FOUQUIER J.P.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	